

Claims:

1. The use of a combination of erucamide and one or more wax(es) in toners.
5
2. The use as claimed in claim 1, wherein the wax is selected from the group consisting of natural waxes and partially synthetic waxes.
3. The use as claimed in claim 1 or 2, wherein the wax has a needle
10 penetration of not more than 10 mm^{-1} .
4. The use as claimed in one or more of claims 1 to 3, wherein the wax has a melting point of from 50 to 160°C .
- 15 5. A toner comprising a combination of erucamide and one or more wax(es).
6. The toner as claimed in claim 5, wherein the wax is selected from the group consisting of natural waxes and partially synthetic waxes.
20
7. The toner as claimed in claim 5 or 6, wherein the wax has a needle penetration of not more than 10 mm^{-1} .
8. The toner as claimed in one or more of claims 5 to 7, wherein the
25 wax has a melting point of from 50 to 160°C .